

Technical Sheet

VizLite™ 201HA Silver Reflective Transfer Film

Product Information

VizLite™ 201HA Silver Reflective Transfer Film is intended for use in the PPE market for the inclusion in High Visibility Warning clothing such as EN ISO 20471:2013 and ANSI Jackets and Waistcoats to enhance visibility in low light and night time conditions.

VizLite™ 201HA Silver Reflective Transfer Film can also be converted to produce reflective logos, badges, trims etc. to be applied to a range of garments and accessories used to enhance visibility.

Design Features

The film is constructed of a layer of microscopic retro reflective glass beads bonded onto a Polymer layer, to which a heat activated adhesive is applied.

VizLite™ 201HA Silver Reflective Transfer Film comes with a PET protective film on the reflective side. In summer months a thin blue PU liner is used on the adhesive side to prevent the adhesive from fusing in high temperatures. This blue liner should always be removed prior to heat application.

When a beam of light from an oncoming vehicle meets the material, the light reflects back to the light source and enhances the visibility of the wearer to the vehicle driver.

Product Performance and Certification

VizLite™ 201HA Silver Reflective Transfer Film is certified by Centro Tessile Cotoniero e Abbigliamento Laboratory in Italy and SATRA in the UK to the following standards.

EN ISO 20471:2013 (High Visibility Warning Clothing)

ANSI/ISEA 107-2004 (High Visibility Safety Apparel)

Retro-reflective Performance

VizLite™ 201HA Silver Reflective Transfer Film;

- Meets and exceeds the levels of brightness required under EN ISO 20471:2013 and ANSI /ISEA 107
- Is non-orientation sensitive
- Offers excellent feel and smoothness
- Is washable to 60°C Domestic wash up to 50 wash cycles including Tumble Dry maximum temperature 60°C
- Is Dry cleanable up to 10 times with perchlorethylene

Ecological Performance

VizLite™ 201HA has been certified by Shirley Technologies in the England to Oeko-Tex Standard 100, product class II have shown that the above mentioned goods meet the human-ecological requirements of the standard presently established for products with direct contact with skin.

The certified articles fulfil the requirements of Annex XVII of REACH (incl. the use of azo-dyes, nickel, etc) as well as the American requirement regarding total content of lead in children's articles (CPSIA)

Product Application

Retro reflective warning garments are mainly used in environments where the wearer is working alongside vehicles. These garments improve visibility of the wearer and thus reduce the risk of being struck by a vehicle e.g. highways, railway lines, airports, warehouses, dockyards.

VizLite™ 201HA reflective material is a durable material tested to wash a minimum of 50 washes in a domestic environment so is also suitable for non-occupational applications such as sportswear and clothing for cyclists, children, pets and pedestrians.

VizLite™ 201HA is not recommended for use in garments used in heavy wear environments and is not suitable for industrial laundry.

Technical Sheet

VizLite™ 201HA Silver Reflective Transfer Film

Product Converting

In addition to the use on EN ISO 20471:2013 and ANSI/ISEA 107-2004 compliant garments, VizLite™ 201HA Reflective Transfer Film is suitable for the production of reflective logos, Badges and trims using the following methods.

Cutting

Cuts should be made from the non-reflective surface and fabric should not be stacked more than 5 cm in height. Fabric is suitable for cutting by,

- Hand (using very sharp cutting tools)
- Guillotine
- Die-cut
- Plotter-cutting
- Kiss cutting

Substrates

The following should be taken into account when applying VizLite™ 201HA Reflective Transfer Film to the substrates listed below,

- On Nylon and other Polyamide substrates, heat application is not suitable and results are poor.
- To avoid damage to the surface of coated substrates the lamination temperature may need adjusting to a lower setting.
- The use of substrates which have had a silicon, fluorocarbon or flame retardant finish may result in poor adhesion.

Lamination

The following recommendations for lamination by using a continual belt heat press and are for guidance only. Other methods can also be used such as heat fusing, HF welding etc. Converters should determine which process best suits their application.

For continual heat press e.g. Reliant heat press,

- Nip roller pressure should be even
- Nip roller pressure ideally set at 70psi (approx 5 bar)
- Machine speed should be set so that the panel is in the tunnel for approx. 12 seconds
- Temperature should be set at 150°C
- Temperature inside of tunnel should be checked used a temperature strip.
- Remove the blue liner if present
- Place the VizLite™ 201HA Reflective Transfer Film with adhesive side down on the substrate.
- Do not apply Transfer film over seams or stitching.
- Delicate fabrics should be protected by placing a siliconised sheet or cloth cover over the film and fabric during lamination.
- The PET Liner should be split when cold by gently lifting from one corner.

Silk Screen Printing

- VizLite™ 201HA Reflective Transfer Film is not suitable for silk screen printing. Use VizLite™ 201 HAP Reflective Transfer Film for printing using either silk screen or rotary equipment.

Technical Sheet

VizLite™ 201HA Silver Reflective Transfer Film

Storage and shipping

- Rolls should be stored in the packaging they are supplied in.
- Cut pieces should be stored flat
- Opened rolls should either be stored in their original packaging or suspended by the use of a rod through the middle of the roll.
- VizLite™ 201HA film should be stored in an area that is cool, dry and with low humidity.
- Precautions should be taken to protect the material from coming into contact with perspiration, strong acids, or compounds containing high levels of sulphur or chlorine.
- Contamination by these substances may affect the aesthetic appearance of the VizLite™ 201HA film.
- During Transportation and Shipping it is best to keep an ambient condition.

Handling

- VizLite™ 201HA film should be handled carefully in hot and humid conditions.
- The area in which the materials are handled may need the need of cooling or dehumidifying equipment to keep the area cool and dry.
- Avoid the contamination of the product with dirt, grease or solvents as this could produce staining that will affect the retro-reflective qualities of the fabric.

Wash and Care

VizLite™ 201HA film is designed to be washed at 60°C in a Domestic wash, up to a minimum 50 cycles before the retro-reflective qualities are affected. However the following domestic washing instructions should be closely followed;

- Do not pre-soak
- Do not use a pre-wash program
- Recommended wash program is for coloured clothing wash
- Do not wash at a higher temperature than 60°C
- Recommended wash Temperature is 30-60°C
- Maximum Program time 50 minutes

- Maximum wash time at highest wash temperature 12 minutes
- Domestic washing powders for delicate and coloured fabrics are recommended

Stain removal

VizLite™ 201HA material should be tested for wash conditions once applied to the substrate. This can be achieved by mixing a solution of detergent and water and applying with a sponge or cloth. For stain removal of grease or mineral oils, use a clean cloth dipped into white spirits. Wipe clean with water afterwards.

- Chemical splashes should be removed with a clean dry cloth.
- Neutralise splashes of strong acid or alkalis immediately with plenty of clean water
- Dispose any material that comes into contact with toxic or harmful substances in a safe and responsible manner.

Do not use the following types of products to clean/treat stains on this garment;

- Heavy duty products or stain removal products with a high alkaline content.
- Micro-emulsions or high pH-products
- Bleaches
- Aromatic solvents

The use of the above will affect the lifespan of the retro-reflective material.

Ironing

- Iron on reverse of material if possible
- Iron using medium heat setting.
- Do not use steam

Specialist cleaning and dry cleaning

- VizLite™ 201HA fabric is not suitable for Industrial laundry methods
- VizLite™ 201HA material is suitable for dry cleaning up to 6 times

Technical Sheet

VizLite™ 201HA Silver Reflective Transfer Film

Drying

- Line drying is the preferred method of drying
- This product can be tumble dried at a maximum temperature of 60°C up to 50 times.

Maintenance issues

VizLite™ 201HA's retro-reflective properties will be affected by any of the following treatments;

- Coating or Spraying the garment with oils, protective waxes, paints or inks.
- Application of products such as leather spray or waxes.
- Harsh physical application of abrasive wire brushes or sand paper.

High Visibility Warning clothes should be inspected regularly and maintained in good condition. Any signs of wear and tear may affect the performance of the garment in relation to EN ISO 20471:2013 or ANSI/ISA.

If the performance of the retro reflective material falls below $R = 100 \text{ cd/lx/m}^2$ the garment should be replaced.

Product Disposal

VizLite™ 201HA film can be disposed of on the garment. The product can be incinerated in a commercial or industrial facility or sent to a landfill site.

General Safety Information

Visibility Limits of VizLite™ 201HA fabrics

There are various uncontrollable environmental factors that will affect visibility; these include smoke, hail, snow, mist, dust and fog. Fog, smoke, mist, and dust can all affect the dispersal of light from headlights and retro reflective performance.

The VizLite™ 201HA film is tested for performance during exposure to rainfall, and exceeds the requirements of EN ISO 20471:2013 and ANSI/ISA. Brightness levels will return after the material dries out.

The retro-reflective qualities can also be diminished by the wearer depending on issues such as the line of sight, other equipment and obstacles in the working environment, and not wearing the garment fastened. The wearer should be aware of these limitations and take the necessary action.

Important notice to Purchaser / Converter / Wearer

Because of the unlimited variety of potential applications for products, BEFORE product use the converter and/ or product manufacturer must determine that the products are suitable for the intended use and are compatible with other component materials. The Purchaser is solely responsible for determining the proper amount and placement of products. While reflective products enhance visibility, no reflective product can ensure visibility on safety under all possible conditions. Neither Viz Reflectives or any Viz Reflectives authorised converter shall be liable for any incidental, special or consequential damages relating to the use or inability to use the products regardless of legal theory used.